

## Epilox<sup>®</sup> M 995

### Description

Epilox<sup>®</sup> M 995 is a water-dispersible epoxy resin.

### Data

Viscosity at 25 °C                      mPa·s                      1100 - 1500  
(DIN 53 015)

Epoxy Equivalent Weight              g                              180 - 195  
(DIN 16 945)

Colour Number (Gardner)                      < 2  
(DIN ISO 4630)

### Uses

Epilox<sup>®</sup> M 995 is processed with suitable curing agents for water-dilutable epoxy resin systems. Main applications are as cold curing epoxy resin systems in civil engineering for protective coatings and paints.

### Packing/Storage/ Transportation

Epilox<sup>®</sup> M 995 is supplied in drums and containers.  
The product should be stored in closed containers at temperatures between 10 and 30 °C to protect it from moisture. Under these storage conditions, Epilox<sup>®</sup> M 995 shows no change in quality even after prolonged storage time exceeding 12 months.

### Safety Requirements

Please refer to the valid Material Safety Data Sheet as well as to the legal and recommended industrial hygiene regulations.

The information given in these data is based on the testing methods established by Leuna-Harze GmbH and on the knowledge of the characteristics of Epilox<sup>®</sup>-resins and Epilox<sup>®</sup>-hardeners and is given in good faith. No liability is accepted by Leuna-Harze GmbH for any system or application in which Epilox<sup>®</sup>-resins and Epilox<sup>®</sup>-hardeners are utilized.